

## Linerboard

WestRock Linerboard is specified to meet burst or high performance strength requirements for greater flexibility in designing traditional class stamped or ECT packaging. Available with either 100% recycled or a blend of virgin and recycled fiber.

- Offered in a range of basis weights from 26# through 90#.
- Optimized for production of high performance packaging structures.
- ISO certified mills.

	26	33	42	69	90
Grade Code	KL26	KL33	KL42	KL69	KL90
<b>Conditioned Basis Wt. (7.5%<math>H_2O</math>), lbs/1000sf Tappi T 410</b>					
Nominal	26	33	42	69	90
Reject Below	24.7	31.4	39.9	65.6	85.5
<b>Moisture Content, % Tappi T 412</b>					
Average (%)	7.5	7.5	7.5	7.5	7.5
Range (+/-)	1.5	1.5	1.5	1.5	1.5
Average (%) - Tacoma Mill	7.0	7.0	7.0	7.0	7.0
<b>Mullen, psi Tappi T 807</b>					
Reject Below	60	72	95	128	155
<b>SCT-CD (STFI) lb<sub>f</sub>/in Tappi T 826</b>					
Reject Below	11.6	14.6	18.4	28.4	38.0
<b>Porosity (Gurley), sec/100cc Tappi T 460</b>					
Reject Below	12	12	12	12	12
<b>Internal Bond, ft-lb/in<sup>2</sup> Tappi T 569</b>					
Scott Bond - Reject Below	75	75	75	75	75
<b>Slide Angle (Degrees) Tappi T 815</b>					
Reject Below	18	18	18	18	18
<b>Cobb 2 Minute (TOP), g/m<sup>2</sup> Tappi T 441</b>					
Reject Above	75	75	75	75	75
Reject Below	30	30	30	30	30