

Coated White Top Linerboard

WestRock Coated White Top Linerboard is designed for high graphics users who need the ability to generate high-print gloss and ink density. It is post-printable without the aid of dryers, yet suitable for the demands of preprinters. Our lightly coated white top offers superior runnability and convertibility, with the compression strength of regular white tops.

	28.7	31	33	37	41	46	51.2
Grade Code	CW287LT	CW31LT	CW33LT	CW37LT	CW41LT	CW46LT	CW51LT
Conditioned Basis Wt. (7.5%H₂O), lbs/1000sf							
<i>Tappi T 410</i>							
Nominal	28.7	31	33	37	41	46	51.2
Reject Above	30.2	32.5	34.5	39.0	43.0	48.0	53.3
Reject Below	27.2	29.5	31.4	35.0	39.0	44.0	49.1
Moisture Content, %							
<i>Tappi T 412</i>							
Average (%)	6.6	6.6	6.6	6.6	6.6	6.6	6.6
Range (+/-)	-1.1/+1.5	-1.1/+1.5	-1.1/+1.5	-1.1/+1.5	-1.1/+1.5	-1.1/+1.5	-1.1/+1.5
STC-CD (STFI) lb_f/in							
<i>Tappi T 826</i>							
Reject Below	—	—	14.6	16.4	18.0	20.4	25.3
Typical*	16.8	17.3	19.1	20.8	22.3	25.4	28.6
Porosity (Gurley), sec/100cc							
<i>Tappi T 460</i>							
Reject Below	30	30	30	30	30	30	30
Cobb 30 Minute (TOP), g/m²							
<i>Tappi T 441</i>							
Reject Above	155	155	155	155	155	155	155
Smoothness, PPS							
<i>Tappi T 555</i>							
Typical	3.0	3.0	2.8	2.8	2.8	3.0	3.3
Reject Above	3.3	3.3	3.1	3.1	3.1	3.3	3.6
Brightness, %							
<i>ISO 2469 & 2470</i>							
Average (%)	80	80	80	80	80	80	80
Range (+/-)	2	2	2	2	2	2	2
Caliper, mils							
<i>Tappi T 411</i>							
Average	5.6	6.5	6.7	7.7	8.1	8.8	9.8
Typical CD Roll Variability	+/- 1	+/- 1	+/- 1	+/- 1	+/- 1	+/- 1	+/- 1

*Typical values are the long term averages for the particular product property and are not a guarantee of performance for individual reels or for production lots.