

## Wet Strength Linerboard

WestRock Wet Strength Linerboard is designed to provide added strength under damp conditions – beneficial for packaging that must undergo extreme transport or storage conditions.

- Available with either 100% recycled or a blend of virgin and recycled fiber.
- Optimized for production of high performance packaging structures.
- ISO certified mills.

	90
Grade Code	KL90WS
<b>Conditioned Basis Wt. (7.5%<math>H_2O</math>), lbs/ 1000sf</b> <b>Tappi T 410</b>	
Nominal	90
Reject Below	85.5
<b>Moisture Content, %</b> <b>Tappi T 412</b>	
Average (%)	7.5
Range (+/-)	1.5
<b>Mullen (Dry), psi</b> <b>Tappi T 807</b>	
Reject Below	155
<b>Mullen (Wet), psi</b> <b>Tappi T 807</b>	
Reject Below	54
<b>SCT-CD (STFI) lb<sub>f</sub>/in</b> <b>Tappi T 826</b>	
Reject Below	38.0
<b>Porosity (Gurley), sec/ 100cc</b> <b>Tappi T 460</b>	
Reject Below	12
<b>Internal Bond, ft-lb/in<sup>2</sup></b> <b>Tappi T 569</b>	
Scott Bond - Reject Below	75
<b>Slide Angle (Degrees)</b> <b>Tappi T 815</b>	
Reject Below	18
<b>Cobb 2 Minute (TOP), g/m<sup>2</sup></b> <b>Tappi T 441</b>	
Reject Above	75
Reject Below	30