

Wet Strength White Top Linerboard

WestRock Wet Strength White Top Linerboard is a multi-ply sheet with a white printing surface over a kraft base sheet. Produced at ISO certified mills, this white top grade is designed to provide added strength under damp conditions and is beneficial for post print or direct print packaging that must undergo extreme transport or storage conditions.

| | 35HP | 42 | 56HP |
|--|----------|----------|----------|
| Grade Code | WT35HPWS | WT42HSWS | WT56HPWS |
| Conditioned Basis Wt. (7.5%H_2O), lbs/1000sf <i>Tappi T 410</i> | | | |
| Nominal | 35 | 42 | 56.7 |
| Reject Below | 33.3 | 40.3 | 54 |
| Moisture Content, % <i>Tappi T 412</i> | | | |
| Reject Above | 8.5 | 8.5 | 8.5 |
| Reject Below | 5.5 | 5.5 | 5.5 |
| Wet Mullen psi <i>Tappi T 807</i> | | | |
| Reject Below - Tacoma | 20.4 | 26 | 36 |
| SCT-CD (STFI) lb_f/in <i>Tappi T 826</i> | | | |
| Reject Below | 18.4 | 18.4 | 28.4 |
| Porosity (Gurley), sec/100cc <i>Tappi T 460</i> | | | |
| Reject Below | 15 | 15 | 15 |
| Internal Bond, Scott <i>Tappi 569</i> | | | |
| Peel - Reject Below | 95 | 105 | 115 |
| Cobb 30 Minute (TOP), g/m² <i>Tappi T 441</i> | | | |
| Reject Above | 155 | 155 | 155 |
| Brightness, % <i>ISO 2469 & 2470</i> | | | |
| Reject Below | 72.5 | 72.5 | 72.5 |