

# Kraft Paper Specifications

## Bleached Butcher Wrap



### Grade Availability by Basis Weight

Conditioned Basis Weight				Units	Method
<b>Nominal</b>	38.0	40.0	47.0	lb/3000 sq. ft.	T-410
<b>Reject Below</b>	36.1	38.0	44.7	lb/3000 sq. ft.	T-410
<b>Reject Above</b>	39.9	42.0	49.4	lb/3000 sq. ft.	T-410
<b>Brightness</b>					
<b>Reject Below</b>	74	74	74	percent	ISO2469
<b>Moisture Content</b>					
<b>Nominal</b>	4.5	4.5	4.5	percent	T-412
<b>Reject Below</b>	2.5	2.5	2.5	percent	T-412
<b>Tensile</b>					
<b>CD Tensile – Reject Below</b>	11.4	12.0	14.0	lb/in	T-494
<b>Total Tensile – Reject Below</b>	35.0	37.0	44.0	lb/in	T-494
<b>HST (70%)</b>					
<b>Reject Below</b>	40	40	40	seconds	T-530

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

# Kraft Paper Specifications

## Pink Butcher Wrap



### Grade Availability by Basis Weight

Conditioned Basis Weight				Units	Method
<b>Nominal</b>	38.0	40.0	47.0	lb/3000 sq. ft.	T-410
<b>Reject Below</b>	36.1	38.0	44.7	lb/3000 sq. ft.	T-410
<b>Reject Above</b>	39.9	42.0	49.4	lb/3000 sq. ft.	T-410
Moisture Content					
<b>Nominal</b>	4.5	4.5	4.5	percent	T-412
<b>Reject Below</b>	2.5	2.5	2.5	percent	T-412
Tensile					
<b>CD Tensile – Reject Below</b>	11.4	12.0	14.0	lb/in	T-494
<b>Total Tensile – Reject Below</b>	35.0	37.0	44.0	lb/in	T-494
HST (70%)					
<b>Reject Below</b>	40	40	40	seconds	T-530

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

# Kraft Paper Specifications

## Kraft Grease Resistant Paper



### Grade Availability by Basis Weight

Conditioned Basis Weight		Units		Method
<b>Nominal</b>	40.0	50.0	lb/3000 sq. ft.	T-410
<b>Reject Below</b>	38.0	47.5	lb/3000 sq. ft.	T-410
<b>Reject Above</b>	42.0	52.5	lb/3000 sq. ft.	T-410
Moisture Content				
<b>Nominal</b>	5.5	5.5	percent	T-412
<b>Reject Below</b>	2.5	2.5	percent	T-412
Tear				
<b>MD Tear – Reject Below</b>	78	90	gf (16-plies)	T-414
<b>Total Tear – Reject Below</b>	160	194	gf (16-plies)	T-494
Tensile				
<b>CD Tensile – Reject Below</b>	12.0	15.3	lb/in	T-494
<b>Total Tensile – Reject Below</b>	37.0	44.0	lb/in	T-494
HST (70%)				
<b>Reject Below</b>	14	19	seconds	T-530
Kit Level				
<b>Reject Below</b>	4	4		

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.