

Kraft Paper Specifications

Bleached Butcher Wrap



Grade Availability by Basis Weight

Conditioned Basis Weight				Units	Method
Nominal	38.0	40.0	47.0	lb/3000 sq. ft.	T-410
Reject Below	36.1	38.0	44.7	lb/3000 sq. ft.	T-410
Reject Above	39.9	42.0	49.4	lb/3000 sq. ft.	T-410
Brightness					
Reject Below	74	74	74	percent	ISO2469
Moisture Content					
Nominal	4.5	4.5	4.5	percent	T-412
Reject Below	2.5	2.5	2.5	percent	T-412
Tensile					
CD Tensile – Reject Below	11.4	12.0	14.0	lb/in	T-494
Total Tensile – Reject Below	35.0	37.0	44.0	lb/in	T-494
HST (70%)					
Reject Below	40	40	40	seconds	T-530

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

Kraft Paper Specifications

Pink Butcher Wrap



Grade Availability by Basis Weight

Conditioned Basis Weight				Units	Method
Nominal	38.0	40.0	47.0	lb/3000 sq. ft.	T-410
Reject Below	36.1	38.0	44.7	lb/3000 sq. ft.	T-410
Reject Above	39.9	42.0	49.4	lb/3000 sq. ft.	T-410
Moisture Content					
Nominal	4.5	4.5	4.5	percent	T-412
Reject Below	2.5	2.5	2.5	percent	T-412
Tensile					
CD Tensile – Reject Below	11.4	12.0	14.0	lb/in	T-494
Total Tensile – Reject Below	35.0	37.0	44.0	lb/in	T-494
HST (70%)					
Reject Below	40	40	40	seconds	T-530

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

Kraft Paper Specifications

Kraft Grease Resistant Paper



Grade Availability by Basis Weight

Conditioned Basis Weight		Units		Method
Nominal	40.0	50.0	lb/3000 sq. ft.	T-410
Reject Below	38.0	47.5	lb/3000 sq. ft.	T-410
Reject Above	42.0	52.5	lb/3000 sq. ft.	T-410
Moisture Content				
Nominal	5.5	5.5	percent	T-412
Reject Below	2.5	2.5	percent	T-412
Tear				
MD Tear – Reject Below	78	90	gf (16-plyes)	T-414
Total Tear – Reject Below	160	194	gf (16-plyes)	T-494
Tensile				
CD Tensile – Reject Below	12.0	15.3	lb/in	T-494
Total Tensile – Reject Below	37.0	44.0	lb/in	T-494
HST (70%)				
Reject Below	14	19	seconds	T-530
Kit Level				
Reject Below	4	4		

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.