

Kraft Paper Specifications

Bleached Multiwall



Grade Availability by Basis Weight

Conditioned Basis Weight						Units	Method
Nominal	40.0	46.0	50.0	60.0	70.0	lb/3000 sq. ft.	T-410
Reject Below	38.0	43.7	47.5	57.9	66.5	lb/3000 sq. ft.	T-410
Reject Above	42.0	48.3	52.5	63.0	73.5	lb/3000 sq. ft.	T-410
Brightness							
Reject Below	74	74	74	74	74	percent	ISO2469
Moisture Content							
Nominal	5.5	5.5	5.5	5.5	5.5	percent	T-412
Reject Below	2.5	2.5	2.5	2.5	2.5	percent	T-412
Tear							
MD Tear – Reject Below	78	88	95	105	122.5	gf (16-plyes)	T-414
Total Tear – Reject Below	168	188	200	225	262.5	gf (16-plyes)	T-414
Tensile							
CD Tensile – Reject Below	12.0	14.1	16.0	20.0	23.3	lb/in	T-494
Total Tensile – Reject Below	37.0	42.0	47.0	58.0	67.7	lb/in	T-494
HST (70%)							
Reject Below	40	40	40	40	40	seconds	T-530

1-10% Recycle

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

Kraft Paper Specifications

Bleached Multiwall – Wet Strength



Grade Availability by Basis Weight

Conditioned Basis Weight				Units	Method
Nominal	50.0	60.0	70.0	lb/3000 sq. ft.	T-410
Reject Below	47.5	57.0	66.5	lb/3000 sq. ft.	T-410
Reject Above	52.5	63.0	73.5	lb/3000 sq. ft.	T-410
Brightness					
Reject Below	74	74	74	percent	ISO2469
Moisture Content					
Nominal	5.5	5.5	5.5	percent	T-412
Reject Below	2.5	2.5	2.5	percent	T-412
Tear					
MD Tear – Reject Below	95	105	122.5	gf (16-plyes)	T-414
Total Tear – Reject Below	200	225	262.5	gf (16-plyes)	T-414
Tensile					
CD Tensile – Reject Below	16.0	20.0	23.3	lb/in	T-494
Total Tensile – Reject Below	47.0	58.0	67.7	lb/in	T-494
CD Wet Tensile – Reject Below	3.0	4.0	4.7	lb/in	T-494
HST (70%)					
Reject Below	40	40	40	seconds	T-530

1-10% Recycle

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

Kraft Paper Specifications

Kraft Multiwall – Wet Strength



Grade Availability by Basis Weight

Conditioned Basis Weight			Units	Method
Nominal	50.0	60.0	lb/3000 sq. ft.	T-410
Reject Below	47.5	57.0	lb/3000 sq. ft.	T-410
Reject Above	52.5	63.0	lb/3000 sq. ft.	T-410
Moisture Content				
Nominal	5.5	5.5	percent	T-412
Reject Below	2.5	2.5	percent	T-412
Tear				
MD Tear – Reject Below	100	122	gf (16-plyes)	T-414
Total Tear – Reject Below	215	262	gf (16-plyes)	T-414
Tensile				
CD Tensile – Reject Below	17	21	lb/in	T-494
Total Tensile – Reject Below	49	60	lb/in	T-494
CD Wet Tensile – Reject Below	3.0	4.0	lb/in	T-494
HST (70%)				
Reject Below	19	24	seconds	T-530

1-10% Recycle

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock’s knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.



Kraft Paper Specifications

Kraft Multiwall



Grade Availability by Basis Weight

Conditioned Basis Weight											Units	Method
Nominal	37.0	40.0	43.0	45.0	46.0	50.0	55.0	60.0	70.0	80.0	lb/3000 sq. ft.	T-410
Reject Below	35.2	38.0	40.9	42.8	43.7	47.5	52.3	57.0	66.5	76.0	lb/3000 sq. ft.	T-410
Reject Above	38.9	42.0	45.2	47.3	48.3	52.5	57.8	63.0	73.5	84.0	lb/3000 sq. ft.	T-410
Moisture Content												
Nominal	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	5.5	percent	T-412
Reject Below	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	percent	T-412
Tear												
MD Tear – Reject Below	70	78	84	89	91	100	111	122	144	168	gf (16-plies)	T-414
Total Tear – Reject Below	153	168	170	170	197	215	239	262	309	355	gf (16-plies)	T-414
Tensile												
CD Tensile – Reject Below	10.5	12.0	13.0	13.2	16.9	17.0	19.0	21.0	25.0	30.0	lb/in	T-494
Total Tensile – Reject Below	33.0	37.0	40.0	40.2	49.1	49.0	54.5	60.0	70.0	84.5	lb/in	T-494
HST (70%)												
Reject Below	14	14	14	19	19	19	24	24	24	24	seconds	T-530

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

Kraft Paper Specifications

Kraft Multiwall – High Tensile



Grade Availability by Basis Weight

Conditioned Basis Weight		Units	Method
Nominal	46.0	lb/3000 sq. ft.	T-410
Reject Below	43.7	lb/3000 sq. ft.	T-410
Reject Above	48.3	lb/3000 sq. ft.	T-410
Moisture Content			
Nominal	5.5	percent	T-412
Reject Below	2.5	percent	T-412
Tear			
MD Tear – Reject Below	90	gf (16-plies)	T-414
Total Tear – Reject Below	185	gf (16-plies)	T-414
Tensile			
CD Tensile – Reject Below	18.3	lb/in	T-494
Total Tensile – Reject Below	47.0	lb/in	T-494
HST (70%)			
Reject Below	19	seconds	T-530

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificates Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751 FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.