

WestRock  
**TruServ™**  
**Uncoated Platestock**  
**Practical paperboard for a range of uses.**

WestRock TruServ™ Uncoated Platestock paperboard is a prime example of smart economics. This practical, basic white offering provides great flexibility at a competitive price point. Mixes can accommodate needs ranging from plates for lightweight meals to plates for heavier options. Also, using renewable, repulpable fibers can help you achieve your sustainability goals.



**Packaging uses**

Disposable Plates

**Product Classification**

Solid Bleached Sulfate

SBS Uncoated Paperboard

**What You Can Expect from Us**

**Purity** TruServ Uncoated Platestock paperboard meets rigorous FDA and Dairyman’s Standards for direct food contact. It is an extremely flexible and safe option for disposable products when cleanliness and purity are important.

**Environmentally Responsible** It is renewable and repulpable making it an environmentally friendly alternative to polystyrene foam products.

**Efficient Design** TruServ Uncoated Platestock paperboard is an economical alternative for light, non-greasy meals.

**Microwave Stable** Unlike plastic alternatives, paperboard resists warping and degradation in the microwave environment.

**Additional Product Information**

**Sustainability** Recyclable. All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product.

**Food Contact** Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses. Kosher documentation available.

**Quality** Produced at an ISO 9001 certified facility.

**Environmental and Safety** Notices under US California Proposition 65 and the EU REACH regulation are not required. Elemental chlorine free (ECF) bleached fiber. Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

**Grade Availability & Typical Properties**  
**Evadale, Texas Mill**

**TruServ™**  
**Uncoated Platestock**

Grade Availability by Caliper					Units	Method
<b>Caliper (pts)</b>	<b>U.S.</b>	0.010	0.011	0.012	inches	T-411
<b>Thickness</b>	<b>Metric</b>	254	279	305	microns	T-411
<b>Nominal Basis</b>	<b>U.S.</b>	100	110	120	lbs/3000 sq ft	T-410
<b>Weight</b>	<b>Metric</b>	163	179	195	gsm	T-410
<b>Moisture</b>		6.0	6.0	6.0	percent	T-412
<b>GE Brightness</b>		83	83	83	percent	T-452
<b>Smoothness</b>						
<b>Sheffield</b>	<b>Wire</b>	335	340	340	mL/min	T-538
	<b>Felt</b>	330	330	330	mL/min	T-538

**Grade Availability & Typical Properties**  
**La Tuque, Quebec Mill**

Grade Availability by Weight			Units	Method	
<b>Caliper (pts)</b>		0.010	0.012	inches	T-410
<b>Nominal Basis Weight</b>		100	120	lbs/3000 sq ft	T-410
<b>Moisture</b>		6.0	6.0	percent	T-412
<b>GE Brightness</b>		82	82	percent	ISO469 & ISO2470
<b>Cobb</b>					
<b>Target</b>		45	45	g/m <sup>2</sup>	T-441

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificate Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751, FSC Company Code: FSC-C104002

© 2017 WestRock Company. WestRock® and TruServ™ are trademarks of WestRock Company. All rights reserved worldwide.

