

CartonMate® C2S-HC

Consistent performance with a backside coating.



If you're looking for best-in-class printing performance with added functionality, look no further than CartonMate® C2S-HC. With a heavy backside coating and exceptional printability, CartonMate C2S-HC gives you smooth, consistent imaging with improved holdout performance that is ideal for a variety of food and healthcare applications.

Packaging uses

- Food Packaging
- Foodservice
- Healthcare
- Pharmaceutical Packaging

Product Classification

- Solid Bleached Sulfate
- SBS Paperboard
- GZ

What You Can Expect from Us

- Consistency** Maximized uniformity and efficiency on converting and filling equipment.
- Surface Uniformity** A smooth surface for consistent printability.
- Fade Resistance** Class white styling without optical brightening agents (OBA) means maximum whiteness without fading.
- Backside Coating** Heavy backside coating provides improved holdout.

Additional Product Information

- Sustainability** Recyclable. All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product.
- Food Contact** Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses.
- Quality** Produced at an ISO 9001 certified facility.
- Environmental and Safety** Notices under US California Proposition 65 and the EU REACH regulation are not required. Elemental chlorine free (ECF) bleached fiber. Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

Grade Availability & Typical Properties (U.S.)

CartonMate® C2S-HC

Grade Availability by Caliper										Units
Caliper (pts)	0.014	0.015	0.016	0.017	0.018	0.020	0.022	0.024		inches
Nominal Basis Weight	173	182	191	203	209	227	245	260		lbs/3000 sq ft
ZDT	44	42	42	40	40	39	39	38		psi
Moisture	6.0	6.0	6.0	6.0	6.0	6.0	6.0	6.0		percent
Stiffness										
Taber 15°	MD	130	155	180	210	245	315	395	495	gf-cm
	CD	60	70	80	95	110	145	185	230	gf-cm
GE Brightness										
	86	86	86	86	86	86	86	86	86	percent
Smoothness										
Sheffield	20	22	24	26	28	32	36	40		mL/min
Color										
Hunter	b	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	L-a-b

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificate Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCOC-6S751, FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ and CartonMate® are trademarks of WestRock Company. All rights reserved worldwide.



westrock.com