


# MWare® Print Quality Plate

## Not just good looking. This paperboard is a strong performer, too.



Graphic standards are important to you. So, our MWare® Print Quality Plate delivers great graphics and stellar performance. Its clay coating provides the consistency you seek. Every roll, every order. Furthermore, MWare Print Quality Plate performs well in all types of forming equipment for efficient converting and less waste. With various paperboard combinations and fiber mixes, you can maximize product integrity and customer satisfaction. In short, MWare Print Quality Plate delivers a very attractive performance.

### Packaging uses

Print Quality Plates  
Pressed Bowls

### Product Classification

Solid Bleached Sulfate  
SBS Paperboard

### What You Can Expect from Us

- Strength** Inherent strength properties help prevent cracking or tears. This ensures a better end-user experience.
- Consistency** Consistent roll-to-roll converting performance. This helps you reduce waste and minimize losses.
- Smoothness** Excellent printability. This helps maintain brand consistency and consumer appeal.

### Additional Product Information

- Sustainability** Recyclable. All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product.
- Food Contact** Meets multiple national requirements for food contact packaging, e.g., US, Canada, Germany and the EU. Contact your sales representative for information on specific markets and end uses. ISEGA Certificate available. Kosher documentation available.
- Quality** Produced at an ISO 9001 certified facility.
- Environmental and Safety** Notices under US California Proposition 65 and the EU REACH regulation are not required. Elemental chlorine free (ECF) bleached fiber. Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

## Grade Availability & Typical Properties (U.S.)

## MWare® Print Quality Plate

Grade Availability by Caliper										Units	Method	
<b>Caliper</b>	0.012	0.014	0.015	0.016	0.017	0.018	0.020	0.022	0.024	inches	T-411	
<b>Nominal Basis Weight</b>	145	163	172	182	187	199	212	233	250	lbs/3000 sq ft	T-410	
<b>Moisture</b>	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	percent	T-412	
<b>GE Brightness</b>	84	84	84	84	84	84	84	84	84	percent	T-452	
<b>Smoothness</b>												
<b>Sheffield</b>	40	45	70	80	80	90	100	110	120	mL/min	T-538	
<b>Color</b>												
<b>Hunter</b>	<b>b</b>	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	L-a-b	T-524

## Grade Availability & Typical Properties (Metric)

Grade Availability by Caliper										Units	Method	
<b>Thickness</b>	305	356	381	406	432	457	508	559	610	microns	T-411	
<b>Weight</b>	236	265	280	296	304	324	345	379	407	gsm	T-410	
<b>Moisture</b>	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	5.8	percent	T-412	
<b>GE Brightness</b>	84	84	84	84	84	84	84	84	84	percent	T-452	
<b>Smoothness</b>												
<b>Sheffield</b>	40	45	70	80	80	90	100	110	120	ML/min	T-538	
<b>Color</b>												
<b>Hunter</b>	<b>b</b>	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	L-a-b	T-524

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificate Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751, FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ and MWare® are trademarks of WestRock Company. All rights reserved worldwide.

