

# MWare® Uncoated Plate

## Practical paperboard for a range of uses.



Our MWare® Uncoated Plate paperboard is a prime example of smart economics. This practical, basic white offering provides great flexibility at a competitive price point. Mixes can accommodate needs ranging from plates for lightweight meals to plates for heavier options. Also, using renewable, repulpable fibers can help you achieve your sustainability goals.

### Packaging uses

Disposable Plates

### Product Classification

Solid Bleached Sulfate

SBS Uncoated Paperboard

### What You Can Expect from Us

#### Purity

Our MWare Uncoated Plate paperboard meets rigorous FDA and Dairyman's Standards for direct food contact. It is an extremely flexible and safe option for disposable products when cleanliness and purity are important.

#### Environmentally Responsible

It is renewable and repulpable making it an environmentally friendly alternative to polystyrene foam products.

#### Efficient Design

MWare Uncoated Plate paperboard is an economical alternative for light, non-greasy meals.

#### Microwave Stable

Unlike plastic alternatives, paperboard resists warping and degradation in the microwave environment.

### Additional Product Information

#### Sustainability

Recyclable.  
All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product.

#### Food Contact

Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses.  
Kosher documentation available.

#### Quality

Produced at an ISO 9001 certified facility.

#### Environmental and Safety

Notices under US California Proposition 65 and the EU REACH regulation are not required.  
Elemental chlorine free (ECF) bleached fiber.  
Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

## Grade Availability & Typical Properties (U.S.)

## MWare® Uncoated Plate

Grade Availability by Caliper				Units	Method	
<b>Caliper</b>	0.010	0.011	0.012	inches	T-411	
<b>Nominal Basis Weight</b>	100	110	120	lbs/3000 sq ft	T-410	
<b>Moisture</b>	6.0	6.0	6.0	percent	T-412	
<b>GE Brightness</b>	83	83	83	percent	T-452	
<b>Smoothness</b>						
<b>Sheffield</b>	<b>Wire</b>	335	340	340	mL/min	T-538
	<b>Felt</b>	330	330	330	mL/min	T-538
<b>Color</b>						
<b>Hunter</b>	<b>b</b>	2.8	2.8	2.8	L-a-b	T-524

## Grade Availability & Typical Properties (Metric)

Grade Availability by Weight				Units	Method	
<b>Thickness</b>	254	279	305	microns	T-411	
<b>Nominal Basis Weight</b>	163	179	195	gsm	T-410	
<b>Moisture</b>	6.0	6.0	6.0	percent	T-412	
<b>GE Brightness</b>	83	83	83	percent	T-452	
<b>Smoothness</b>						
<b>Sheffield</b>	<b>Wire</b>	335	340	340	ML/min	T-489
	<b>Felt</b>	330	330	330	ML/min	T-489
<b>Color</b>						
<b>Hunter</b>	<b>b</b>	2.8	2.8	2.8	L-a-b	T-524

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificate Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCOC-6S751, FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ and MWare® are trademarks of WestRock Company. All rights reserved worldwide.

