

WestRock  
**PrintKote® Release**  
**A nonstick solution for bakers that makes accounting happy, too.**



With WestRock PrintKote® Release, bakeries can bake and serve on a single, printable container and achieve best in class product release. This can result in an immediate reduction of packaging and operational costs. PrintKote Release works with both conventional and microwave ovens. It also resists moisture, oil, and grease and can be customised to fit your specific needs. Formed into a variety of configurations, PrintKote Release can be customised to address the needs of both in-store and institutional bakeries.

**Region**

EMEA (Europe, the Middle East and Africa)

**Packaging uses**

Food Packaging for Bakery  
 Foodservice for Bakery

**Product Classification**

Polymer-Coated  
 Solid Bleached Sulfate  
 SBS Paperboard  
 GZ

**What You Can Expect from Us**

- Nonstick Polymer** An innovative polymer coating creates superior release for bakery products.
- Multiple Uses** Can be used for freezing, baking and serving, which eliminates the need to repack products from pan to retail carton and wash cookware.
- Thermal Stability** Excellent heat resistance means reduced warping and twisting relative to competitive coated paperboards.
- Consistency** Roll-to-roll and sheet-to-sheet uniformity increases efficiency on high-speed forming and filling lines.
- Printability** A clay-coated exterior yields a smooth, consistent surface for high-quality printing.

**Additional Product Information**

- Chain of Custody** 100% PEFC™ Certified - BV/CDC/0575784
- Food Contact** Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses. Kosher documentation available.
- Quality** Produced at an ISO 9001 certified facility.
- Environmental and Safety** Notices under US California Proposition 65 and the EU REACH regulation are not required. Elemental chlorine free (ECF) bleached fibre. Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

## Grade Availability (EMEA) & Typical Properties

PrintKote® Release

Grade Availability					Units	Method	Tolerance	
<b>Nominal Basis Weight</b>	265	296	324	345	gsm	T-410		
<b>Caliper (pts)</b>	0.014	0.016	0.018	0.020	inches	T-411	+/- .001	
<b>Thickness</b>	356	406	457	508	microns	T-411	+/-25.4	
<b>Moisture</b>	5.3	5.6	5.6	5.6	percent	T-412		
<b>Internal Bond</b>	147	147	147	158	J/m <sup>2</sup>	T-569		
<b>Stiffness</b>								
<b>Taber 15°</b>	<b>MD</b>	11.8	16.7	21.6	27.5	mNm	T-489	+/- 15%
	<b>CD</b>	5.9	9.3	11.8	15.2	mNm	T-489	+/- 15%
<b>Coated Side</b>								
<b>GE Brightness</b>	86	86	86	86	percent	T-452		
<b>Parker Print</b>	1.0	1.2	1.2	1.2	µm	T-555		
<b>ZDT</b>	324	276	276	276	kPa	T-541		
<b>Colour</b>								
<b>Hunter</b>	<b>L</b>	93	93	93	93	L-a-b	T-524	
	<b>a</b>	-0.8	-0.8	-0.8	-0.8	L-a-b	T-524	
	<b>b</b>	1.5	1.5	1.5	1.5	L-a-b	T-524	

Values are for basestock only; for nominal basis weight including polymer, add 15 gsm.

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

© 2018 WestRock Company. WestRock® and PrintKote® are trademarks of WestRock Company. All rights reserved worldwide.



[westrock.com](http://westrock.com)