


WestRock TruServ™ Poly Cupstock

The performance you seek.
The consistency you want.



Our WestRock TruServ™ Poly Cupstock shines in regard to strength and consistency. It works well with all types of forming equipment. And ultimately it helps reduce costs and promote efficiency. Depending on your performance and sustainability goals, we deliver various offerings of fibre mix and functional coatings—all of which meet strict global food standards. This strong paperboard cupstock helps resist cracks and tears, which greatly improves the consumer experience.

Region

EMEA (Europe, the Middle East and Africa)

Packaging uses

Hot Beverage Cups
Cold Beverage Cups
Lidded Food Cups

Product Classification

Polymer-Coated
Solid Bleached Sulfate
SBS Paperboard
GZ

What You Can Expect from Us

- Consistency** We put advanced systems in place to ensure roll-to-roll consistency to improve converting efficiency. This helps reduce converting costs.
- Liquid Holdout** Designed to withstand the liquid holdout challenges associated with new beverage ingredients.
- Cup Machinability** Capable of excellent and consistent rim forming in high-speed cup forming.
- PCF Availability** Paperboard options can include up to 15% post-consumer recycled fibre (PCF).

Additional Product Information

- Sustainability** Recycled fibre content available by specification.
- Chain of Custody** 100% PEFC™ Certified - BV/CDC/0575784
- Food Contact** Meets multiple national requirements for food contact packaging, e.g., US, Canada, Germany and the EU. Contact your sales representative for information on specific markets and end uses.
ISEGA Certificate available.
Kosher documentation available.
- Quality** Produced at an ISO 9001 certified facility.
- Environmental and Safety** Notices under US California Proposition 65 and the EU REACH regulation are not required.
Elemental chlorine free (ECF) bleached fibre.
Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

UNCOATED ONLY														BOTTOM STOCK ONLY		P1S ONLY	P2S ONLY	FOR HOT BEVERAGE CUPS ONLY	TruServ™ Poly Cupstock	
Grade Availability (EMEA) & Typical Properties														Units	Method					
Caliper (pts)	U.S.	0.0070	0.0082	0.0093	0.010	0.0113	0.0124	0.0130	0.0150	0.0165	0.0180	.0180	0.0200	inches	T-411					
Thickness	Metric	178	208	236	254	287	315	330	381	419	457	457	508	microns	T-411					
Nominal	U.S.	90	98	120	129	140	143	150	168	175	185	185	212	lbs/3000 sq ft	T-410					
Basis Weight	Metric	147	160	195	210	228	233	244	274	285	301	301	345	gsm	T-410					
Moisture		6.5	6.5	6.5	6.5	6.5	6.5	6.5	6.5	6.7	6.7	6.5	6.5	percent	T-412					
GE Brightness		84	84	84	84	84	84	84	84	84	84	84	84	percent	T-452					
Smoothness																				
Sheffield	Wire	175	200	130	130	175	280	180	225	260	280	280	270	mL/min	T-538					
	Felt	185	215	120	120	160	300	165	190	225	230	190	250	mL/min	T-538					
Stiffness																				
Taber 15° (U.S.)	MD	17	20	40	40	60	76	90	120	165	210	217	310	gf-cm	T-489					
	CD	8	9	18	18	31	32	44	60	76	100	100	150	gf-cm	T-489					
Taber 15° (Metric)	MD	1.7	1.9	3.9	3.9	5.8	7.5	8.8	11.8	16.1	20.5	21.3	30.4	gf-cm	T-489					
	CD	0.8	0.9	1.7	1.7	3.0	3.1	4.3	5.9	7.6	9.8	9.8	14.7	gf-cm	T-489					
Tear																				
Elmendorf	MD	190	200	245	245	250	370	320	310	305	370	370	365	gf	T-414					
	CD	205	235	265	265	310	400	360	365	340	430	430	445	gf	T-414					
Stretch	CD	4.3	6.0	6.0	6.0	5.6	5.8	5.0	5.0	5.4	5.0	5.0	4.7	percent	T-494					
Colour																				
Hunter	L	93.5	93.5	93.5	93.5	93.5	93.5	93.5	93.5	93.5	93.5	91	93.5	L-a-b	T-524					
	a	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3	L-a-b	T-524					
	b	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	3.3	L-a-b	T-524					

Values are for basestock only. A variety of polymer structures and thicknesses are available. Values are subject to change without notice.

LDPE Poly Configurations Available			
Thickness			
Mils (U.S.)	0.50	0.75	1.00
Microns	12.7	19.1	25.4
Basis Weight			
lbs/3000 sq ft (U.S.)	7.2	10.8	14.4
gsm	11.7	17.6	24.0

Corona treatment must be requested if you will print on poly. Standard LDPE one side is 0.75 mils gloss. Standard P2S is 0.75 mils matte/0.5 mils gloss. PLA is 1 mil (30 gsm/18 lbs) P1S or P2S.

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

© 2018 WestRock Company. WestRock® and TruServ™ are trademarks of WestRock Company. All rights reserved worldwide.

