


# WestRock TruServ™ Pressed Tray

## Trays that can take the heat. Not to mention the freeze.



From freezer to oven without missing a beat. That's the advantage you can expect from WestRock TruServ™ Pressed Tray paperboard. It's the ideal solution for frozen trayed meals as well as deli trays, grocery store or convenience store fresh meals, bakery applications and more. SBS-based, this resilient paperboard maintains compliance with strict global food safety standards. It offers a smooth surface that's highly printable so you can create customisable, thermoformed trays.

### Region

EMEA (Europe, the Middle East and Africa)

### Packaging uses

Pressed Food Trays  
Pressed Foodservice Trays

### Product Classification

Polymer-Coated  
Solid Bleached Sulfate  
SBS Paperboard  
Uncoated Paperboard

### What You Can Expect from Us

- Thermal Stability** Extruded with a barrier polymer (available clear) that is engineered to perform from -40°F (-40°C) to 428°F (220°C).
- Moisture Resistance** Withstands the demands of frozen food environments. You can expect it to maintain integrity throughout the cyclical conditions of the cold chain.
- Product Uniformity** A smooth surface provides outstanding ink holdout and best-in-class print consistency. Polymer coat-weight uniformity offers improved efficiencies and maximum forming and filling throughput.
- Heat Sealability** Outstanding heat-sealing performance across a range of technologies, including hot air, platen and microwave. This means you can expect improved efficiency and ultimate flexibility.

### Additional Product Information

- Chain of Custody** 100% PEFC™ Certified - BV/CDC/0575784
- Food Contact** Meets multiple national requirements for food contact packaging, e.g., US, Canada, Germany and the EU. Contact your sales representative for information on specific markets and end uses. ISEGA Certificate available. Kosher documentation available.
- Quality** Produced at an ISO 9001 certified facility.
- Environmental and Safety** Notices under US California Proposition 65 and the EU REACH regulation are not required. Elemental chlorine free (ECF) bleached fibre. Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

## Grade Availability (EMEA) & Typical Properties

## TruServ™ Pressed Tray

Grade Availability				Units	Method	
<b>Nominal Basis Weight</b>	300	330	375	gsm	T-410	
<b>Caliper (pts)</b>	0.0165	0.0180	0.0200	inches	T-411	
<b>Thickness</b>	419	457	508	microns	T-411	
<b>Moisture</b>	9.0	9.5	10.0	percent	T-412	
<b>GE Brightness</b>	84	84	84	percent	T-452	
<b>Stiffness</b>						
<b>Taber 15°</b>	<b>MD</b>	16.2	21.3	26.5	mNm	T-489
	<b>CD</b>	7.5	9.8	13.8	mNm	T-489

Values are for basestock only; for nominal basis weight including polymer, add 40 gsm.  
Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

© 2018 WestRock Company. WestRock® and TruServ™ are trademarks of WestRock Company. All rights reserved worldwide.

