

# WestRock ReNew100™ Angel

## A low-density solution that meets your high expectations.

Looking for a 100% recycled paperboard alternative to virgin grades? Turn to WestRock ReNew100™ Angel coated recycled paperboard (CRB). It's perfectly suited to a wide variety of packaging applications. ReNew100 Angel features best-in-class smoothness for excellent printability.

### Packaging Uses

Cookies, Crackers  
And Snack Foods

Cereals And Other  
Dry Foods

Beauty And  
Personal Care

Healthcare

Film And Foil-  
Laminated  
Packaging

Shipping  
Envelopes

Printer Supplies

Other Non-Food  
Applications

### Product Classification

Coated Recycled  
Paperboard

CRB Paperboard

### What You Can Expect from Us

#### Recycled Fiber Content

Made from 100% recycled fiber, which has been diverted from the waste stream.

#### Smoothness

Best-in-class smoothness for excellent printability.

#### Caliper Range

Available in lower calipers than standard CRB offerings.

#### Strength-to- Weight Ratios

The low density provides brands with additional options to meet your sustainability goals.

### Additional Product Information

#### Sustainability

Made with 100% recycled fiber and is recyclable. All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product.

#### Food Contact

Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses.

#### Environmental And Safety

Notices under US California Proposition 65 and the EU REACH regulation are not required.

Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

## Grade Availability & Typical Properties (U.S.)

ReNew100™ Angel

Grade Availability by Caliper							Units	
Caliper (pts)	0.014	0.016	0.018	0.020	0.022	0.024	inches	
Basis Weight	60	65	72	78	83	89	lbs/MSF	
Stiffness								
Taber 15°	MD	130	180	245	320	385	470	gf-cm
	CD	45	65	85	105	130	155	gf-cm

## Grade Availability & Typical Properties (Metric)

Grade Availability by Weight							Units	
Thickness	356	406	457	508	559	610	microns	
Basis Weight	293	317	352	381	405	435	lbs/MSF	
Stiffness								
Taber 15°	MD	12.7	17.7	24.9	31.4	37.8	46.1	mNm
	CD	4.4	6.4	8.3	10.3	12.8	15.2	mNm

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at [westrock.com](http://westrock.com).

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificate Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCOC-6S751, FSC Company Code: FSC-C104002

© 2018 WestRock Company. WestRock® and ReNew100™ are trademarks of WestRock Company. All rights reserved worldwide. Rev. 9/18



[westrock.com](http://westrock.com)