WestRock

# ReNew100™ Classic
## The classic answer to your sustainability goals.

Made from 100% recycled fiber, WestRock Renew100™ Classic coated recycled paperboard (CRB) is the ideal solution for a wide variety of folding carton and custom applications. A double clay-coated surface provides a clean palette for eye-catching graphics. ReNew100 Classic is available in both news and kraft back.

## Packaging uses

Cookies, Crackers, And Snack Foods

Cereals And Other Dry Foods

Toys And Recreational Products

Electronics

Household Goods

Additional Food And Non-Food Applications

## Product Classification

Coated Recycled Paperboard

CRB Paperboard

## What You Can Expect from Us

| | |
|---|---|
| Recycled Fiber Content | Made from 100% recycled fiber, which has been diverted from the waste stream. |
| Printability | Double clay-coated surface for eye-catching graphics. |
| Versatile Supply | Produced at multiple mills. |
| Consistency | Excellent roll-to-roll consistency. |

## Additional Product Information

| | |
|---|---|
| Sustainability | Made with 100% recycled fiber and is recyclable. All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product. |
| Food Contact | Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses. |
| Environmental and Safety | Notices under US California Proposition 65 and the EU REACH regulation are not required. Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC. |

WestRock

## Grade Availability & Typical Properties (U.S.)

| Grade Availability by Caliper | | | | | | | | | | | Units |
|---|---|---|---|---|---|---|---|---|---|---|---|
| **Caliper (pts)** | | 0.016 | 0.018 | 0.020 | 0.022 | 0.024 | 0.026 | 0.028 | 0.030 | 0.032 | inches |
| **Nominal Basis Weight** | | 69 | 77 | 82 | 88 | 96 | 104 | 112 | 120 | 128 | lbs/MSF |
| **Stiffness** | | | | | | | | | | | |
| **Taber 15°** | **MD** | 155 | 225 | 300 | 395 | 445 | 540 | 655 | 790 | 900 | gf-cm |
| | **CD** | 55 | 80 | 100 | 125 | 145 | 185 | 220 | 250 | 300 | gf-cm |

## Grade Availability & Typical Properties (Metric)

| Grade Availability by Weight | | | | | | | | | | | Units |
|---|---|---|---|---|---|---|---|---|---|---|---|
| **Thickness** | | 406 | 457 | 508 | 559 | 610 | 660 | 711 | 762 | 813 | microns |
| **Nominal Basis Weight** | | 337 | 376 | 400 | 430 | 469 | 508 | 547 | 586 | 625 | gsm |
| **Stiffness** | | | | | | | | | | | |
| **Taber 15°** | **MD** | 15.2 | 22.1 | 29.4 | 38.7 | 43.6 | 53.0 | 64.2 | 77.5 | 88.3 | mNm |
| | **CD** | 5.4 | 7.8 | 9.8 | 12.3 | 14.2 | 18.1 | 21.6 | 24.5 | 29.4 | mNm |

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at westrock.com.