

WestRock ReNew100® Mask

Stain masking without the use of fluoro-chemicals.

WestRock ReNew100® Mask coated recycled board (CRB) is a 100% recycled coated paperboard alternative to off-line coating, extrusions and laminations for select folding carton applications. You can expect superior masking performance that reduces the appearance of oil, fat and grease stains. A double clay-coated surface provides an ample canvas for eye-catching graphics.

Packaging Uses

Cookies, Crackers
And Snack Foods

Cereals And Other
Dry Foods

Foodservice
Takeout Packaging

Pet Foods

Lotion-
Impregnated
Tissue

Industrial Parts

Other Non-Food
Applications

Product Classification

Coated Recycled
Paperboard

CRB Paperboard

What You Can Expect from Us

Recycled Fiber Content

Made from 100% recycled fiber, which has been diverted from the waste stream.

Grease Masking

Oil and grease stains do not show on the outside of the package.

Printability

Offers a smooth, clay-coated surface for eye-catching graphics.

No Fluorocarbons

Does not use fluorocarbons, which are a key sustainability concern to many brands.

Additional Product Information

Sustainability

Made with 100% recycled fiber and is recyclable.
All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product.

Food Contact

Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses.

Environmental and Safety

Notices under US California Proposition 65 and the EU REACH regulation are not required.
Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

Grade Availability & Typical Properties (U.S.)

ReNew100® Mask

Grade Availability by Caliper								Units
Caliper (pts)		0.018	0.020	0.022	0.024	0.026	0.028	inches
Basis Weight		77	82	88	96	104	112	lbs/MSF
Stiffness								
Taber 15°	MD	225	300	395	445	540	655	gf-cm
	CD	80	100	125	145	185	220	gf-cm

Grade Availability & Typical Properties (Metric)

Grade Availability by Weight								Units
Thickness		457	508	559	610	660	711	microns
Basis Weight		376	400	430	469	508	547	gsm
Stiffness								
Taber 15°	MD	22.0	29.4	38.7	43.6	53.0	64.2	mNm
	CD	7.8	9.8	12.3	14.2	18.1	21.6	mNm

Values subject to change without notice.

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificate Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCCOC-6S751, FSC Company Code: FSC-C104002

© 2019 WestRock Company. WestRock® and ReNew100® are trademarks of WestRock Company. All rights reserved worldwide. Rev. 7/19



westrock.com