

Uncoated Platestock

Practical paperboard for a range of uses.



Our Uncoated Platestock paperboard is a prime example of smart economics. This practical, basic white offering provides great flexibility at a competitive price point. Fiber mixes can accommodate needs ranging from plates for lightweight meals to plates for heavier options. Also, using renewable, repulpable fibers can help you achieve your sustainability goals.

Packaging uses

Uncoated
Disposable Plates

Product Classification

Solid Bleached
Sulfate

SBS Uncoated
Paperboard

What You Can Expect from Us

Purity

Our Uncoated Platestock paperboard meets rigorous FDA and Dairyman's Standards for direct food contact. It is an extremely flexible and safe option for disposable products when cleanliness and purity are important.

Environmentally Responsible

It is renewable and repulpable making it an environmentally friendly alternative to polystyrene foam products.

Efficient Design

Uncoated Platestock paperboard is an economical alternative for light, non-greasy meals.

Microwave Stable

Unlike plastic alternatives, paperboard resists warping and degradation in the microwave environment.

Additional Product Information

Sustainability

Recyclable.
All WestRock North American paperboard mills are certified to the SFI®, PEFC™, FSC™ Chain of Custody Standards. Contact your WestRock sales representative for certified fiber availability for this product.

Food Contact

Meets multiple national requirements for food contact packaging, e.g., US and Canada. Contact your sales representative for information on specific markets and end uses.

Quality

Produced at an ISO 9001 certified facility.

Environmental and Safety

Notices under US California Proposition 65 and the EU REACH regulation are not required.
Elemental chlorine free (ECF) bleached fiber.
Meets heavy metal limits of the US Model Toxics in Packaging rules and Article 11 of EU Directive 94/62/EC.

Grade Availability & Typical Properties (U.S.)

Uncoated Platestock

Grade Availability by Caliper			Units	Method
Caliper (pts)	0.010	0.012	inches	T-410
Nominal Basis Weight	100	120	lbs/3000 sq ft	T-410
Reject Below	95.2	115.5	lbs/3000 sq ft	T-410
Moisture				
Average	6.0	6.0	percent	T-412
Range (+/-)	2.0	2.0	percent	T-412
Brightness				
Target	82	82	percent	ISO469 & ISO2470
Reject Above	78	78	percent	ISO469 & ISO2470
Cobb				
Target	45	45	g/m ²	T-441
Reject Above	65	65	g/m ²	T-441
Caliper, mils				
Average	10	12.0	mils	T-411
Typical CD Roll Variability	+/- 1	+/- 1	mils	T-411
Caliper, micron				
Average	250	305	microns	T-411
Typical CD Roll Variability	+/- 10	+/- 10	microns	T-411

Values are subject to change without notice.

For more information, please contact your WestRock representative or visit our website at westrock.com.

The information contained in this Product Guide is accurate to the best of WestRock's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. WestRock disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. This information is subject to change without notice.

Certificate Codes: SFI Certified Sourcing: NSF-SFI-CS-6S751, SFI CoC: NSF-SFICOC-6S751, PEFC: NSF-PEFCOC-6S751, FSC Company Code: FSC-C104002

© 2016 WestRock Company. WestRock™ is a trademark of WestRock Company. All rights reserved worldwide.

